

Alukett Spezial Fashion

by B & B

Metallic, dry & sparkling

Alukett Spezial Fashion – the fresh feel

Embossed label paper, wet strength and alkali resistant, excellent ink retention in the washing solution, high strength. With functional coating on the reverse. High printing and labelling speed.

Even before it is printed, Alukett Spezial Fashion conveys spontaneity, invigorating with its cool, crisp surface.

As a metallic embossed label paper, Alukett Spezial Fashion gives your product presentation a distinguished feel, setting it apart from the general run in visual terms. Its radiant ink characteristics make Alukett Spezial Fashion a label paper for aspirational beverages seeking the attribute of freshness and clarity. The tangible texture gives the label designer every facility to give the label his personal touch.

What distinguishes Alukett Spezial Fashion from other label papers is its special refraction, its high gloss, and the opaque body of this material.

Its tactile attributes combined with excellent printability and labelling performance thus make it an economic and reliable resource.

Print Information

Very good results in flexo- and offset printing with conventional inks for metallized paper.

Varnishing

Finishing

Suitable for foil and relief stamping. Excellent stamping quality even for demanding shapes (neck labels).

Labelling

Suitable for all common gluing systems. High labelling speed. Excellent glue consumption using functional coating on the reverse. Very good flatness characteristics. For one-way and returnable applications. The handling guidelines from the glue producer have to be followed to achieve optimum labelling results.

Special features

Very good ink retention and short come off time in washing solution.

According guideline 94/62/EG.

Service Information

Standard format stock for small quantities up to 3 tonnes

Format: 72 x 102	71 g/m ²
70 x 100	71 g/m ²
52 x 72	71 g/m ²

B&B holds ISO 9001, ISO 14001, ISO 50001 and HACCP certificates



property	unit	method					tolerance
Substance	g/m ²	ISO 536		68	71		+/- 3%
Caliper	µm	ISO 534, single sheet measurement		63	66		+/- 5%
Smoothness Bekk	Bekk sec.	ISO 5627	RS	< 150	< 150		guide number
Cobb 60"	g/m ²	ISO 535	RS	15	15		+/- 3
Tensile strength dry	N/15mm	ISO 1924-2	MD	55	55		- 10
			CD	39	39		- 7
Tensile strength wet	N/15mm	ISO 3781 10 minutes soaking time	MD	13	14		- 2
			CD	11	12		- 2
Resistance to penetration and come-off time in alkaline solution	Seconds	DIN 16524-6	PT	80	80		max.
Resistance to alkaline solution	Minutes	DIN 16524-7	COT	130	130		max.
Climatic Curl 30 % relative Humidity				60	60		min.
Climatic Curl 50 % relative Humidity	cm	internal instruction QK/40		-1,00	-1,00		guide number
Climatic Curl 80 % relative Humidity				0	0		guide number
relative Humidity	%	Hygromer Rotronic		1,00	1,00		guide number
				50	50		+/-5 at 23°C

Key: CS - coated Side
RS - reverse Side
MD - Machine Direction

CD - Cross Direction
PT – penetration time
COT – come-off time

Testing conditions :
Standard climate EN 20187
23° Celsius, 50 % relative Feuchte

Date of issue: 5-2016

Label Management by B & B

All rights to improve quality due to technical modifications reserved

Made in EU

B&B
LABELS AND FLEXPack