

Utilisations finales : Magazines, catalogues, suppléments, direct mail, encarts/flyers

Caractéristiques de base	ISO				
Grammage	(ISO 536)	(g/m ²)	70	80	90
Épaisseur	(ISO 534)	(µm)	68	76	84
Main	(ISO 534)	(cm ³ /g)	0.97	0.95	0.93
Blancheur D65	(ISO 2470)	(%)	92	94	94
Blancheur CIE	(ISO 11475)	(%)	120	120	120
Luminance	(ISO 5631-2)	(D65/10°)	93	93	93
Valeur A	(ISO 5631-2)	(D65/10°)	1.2	1.2	1.2
Valeur B	(ISO 5631-2)	(D65/10°)	-7.4	-7.4	-7.4
Opacité	(ISO 2471)	(%)	94	95	96
Brillance Lehman	(ISO 8254-1) (Tappi T480)	(%)	28	31	32
Lissé (Rugosité) PPS 10	(ISO 8791-4)	(µm)	2.5	2.5	2.5

Pre-press données	ISO				
CIE L*-valeur**	13655, M1	D50/2°	93	93	93
CIE A*-VALEUR**	13655, M1	D50/2°	0.5	0.5	0.5
CIE b*-valeur**	13655, M1	D50/2°	-3.0	-3.0	-3.0

Recommandé ICC-Profil : FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

MÉTHODE D'IMPRESSION : Heat set web offset

SURFACE : Mat

Paper Profile 2014 PEFC

EU Ecolabel

ISO 14001: 2009 ISO 9001: 2008 ISO 18001: 2007