

Utilisations finales : Magazines, catalogues, suppléments, direct mail, encarts/flyers

Caractéristiques de base	ISO		70 G	80 G	90 G
			70 G	80 G	90 G
Grammage	(ISO 536)	(g/m <sup>2</sup> )	70 ± 4%	80 ± 4%	90 ± 4%
Épaisseur	(ISO 534)	(µm)	90 ± 4	100 ± 4	112 ± 4
Main	(ISO 534)	(cm <sup>3</sup> /g)	1.28	1.25	1.24
Blancheur D65	(ISO 2470-1999)	(%)	98.5 ± 1	98.5 ± 1	98.5 ± 1
Blancheur CIE	(ISO 11475)	(%)	160 ± 5	160 ± 5	160 ± 5
Opacité	(ISO 2471)	(%)	≥ 90	≥ 92	≥ 93

Méthode d'impression : Heatset / Coldset  
Certification PEFC