

PRESSNEWS - Specifications

**Newsprint paper produced from recycled fibres and/or thermomechanical pulp.
Offset printing with or without dryer.**

NEWSPRINTPAPER FOR OFFSET PRINTING WITHOUT DRYER

Grammage (g/m²)	40	42	45	48.8	52 *
D65 whiteness (%)	59	59	59	59	59
ISO opacity (%)	91-93	92-93	93-95	94-96	96-97
Bulk (cm³/g)	1.4-1.7 (depending on fibre composition)				

* On request

Coloured newsprint paper: salmon, yellow, pink. (Other colours on request)

NEWSPRINT PAPER FOR OFFSET PRINTING WITH DRYER

Grammage (g/m²)	40	42	45	48.8	52
D65 whiteness (%)	59	59	59	59	59
ISO opacity (%)	90-93	92-93	92-95	94-96	94-97
Bulk (cm³/g)	1.3	1.3	1.3	1.3	1.3

DIRECTORY PAPER

Grammage (g/m²)	28 *	29.3 *	31 *	32.5 *	34 *	36	38	40
D65 whiteness (%)	55	55	59	60	60	60	60	60
ISO opacity (%)	85	85	86.5	85	86	88	89	90
Bulk (cm³/g)	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5

* On request

Non-contractual data

PRESSPRINT A - Specifications

Enhanced newsprint paper produced from recycled fibres and/or thermomechanical pulp.

Offset printing with or without dryer.

Whiteness (D65) 65

Grammage (g/m²)	42	45	48.8	52	55
ISO opacity (%)	91	92	93	94	94
Bulk (cm³/g)	1.25-1.35	1.25-1.35	1.25-1.35	1.25-1.35	1.25-1.35

WHITENESS (D65) 68

Grammage (g/m²)	42	45	48.8	52	55
ISO opacity (%)	90	90-92	92-94	92-94	94-95
Bulk (cm³/g)	1.2-1.35	1.2-1.35	1.2-1.35	1.2-1.35	1.2-1.35

WHITENESS (D65) 72

Grammage (g/m²)	45	48.8	52	55
ISO opacity (%)	89-92	90-93	92-94	94-95
Bulk (cm³/g)	1.35-1.65	1.35-1.65	1.35-1.65	1.35-1.65

WHITENESS (D65) 76

Grammage (g/m²)	45	48.8	52	55	60
ISO opacity (%)	92	90.5-93	92-94	93-95	94-95
Bulk (cm³/g)	1.35-1.6	1.35-1.6	1.35-1.6	1.35-1.6	1.35-1.6

WHITENESS (D65) 80

Grammage (g/m²)	49*	52	55	60
ISO opacity (%)	89	91.5-92	92-93	93-94
Bulk (cm³/g)	1.5-1.6	1.5-1.6	1.5-1.6	1.5-1.6

* On request

Non-contractual data