

## PRESSLISSE - Specifications

**Supercalendered (SC) paper produced from thermomechanical/chemical pulp and recycled fibres.**

**Offset printing with dryer and rotogravure.**

### B

<b>Grammage (g/m<sup>2</sup>)</b>	<b>36*</b>	<b>38*</b>	<b>40*</b>	<b>42*</b>	<b>45</b>	<b>48.8</b>	<b>52</b>	<b>56</b>	<b>60*</b>
<b>D65 whiteness (%)</b>	68	68	68	68	67-68	67-68	67-68	67-68	68
<b>ISO opacity (%)</b>	87	88	89	90	90-92	91-92	92-93	93-94	95
<b>Hunter gloss (%)</b>	30	30	30	30	35-37	35-40	35-40	35-40	38
<b>Bulk (cm<sup>3</sup>/g)</b>	1.15	1.15	1.15	1.15	0.9	0.9	0.9	0.9	0.9

\* On request

### A

<b>Grammage (g/m<sup>2</sup>)</b>	<b>45</b>	<b>48.8</b>	<b>52</b>	<b>56</b>	<b>60</b>
<b>D65 whiteness (%)</b>	68	68	68	68	68
<b>ISO opacity (%)</b>	85-89	89-91	90-92	92-93	93-94
<b>Hunter gloss (%)</b>	42-48	42-51	44-52	46-52	46-52
<b>Bulk (cm<sup>3</sup>/g)</b>	0.8-0.9	0.8-0.9	0.8-0.9	0.8-0.9	0.8-0.9

### A +

<b>Grammage (g/m<sup>2</sup>)</b>	<b>45</b>	<b>48</b>	<b>51</b>	<b>54</b>	<b>57</b>	<b>60*</b>
<b>D65 whiteness (%)</b>	72	72	72-74	72-75	72	72
<b>ISO opacity (%)</b>	87	87-90	89-92	90-93	91-94	92
<b>Hunter gloss (%)</b>	46	46-50	48-52	48-52	48-52	52
<b>Bulk (cm<sup>3</sup>/g)</b>	0.8-0.9	0.8-0.9	0.8-0.9	0.8-0.9	0.8-0.9	0.8-0.9

\* On request

### A ++

<b>Grammage (g/m<sup>2</sup>)</b>	<b>45</b>	<b>48</b>	<b>51</b>	<b>54</b>	<b>57</b>	<b>60</b>	<b>65</b>	<b>70</b>
<b>D65 whiteness (%)</b>	78	78-80	78-80	78-80	80	80	80	80
<b>ISO opacity (%)</b>	87	88-89	90-91	90-91	91-92	92-93	92	93
<b>Hunter gloss (%)</b>	43	44-45	43-45	46-47	46-48	46-49	47	47
<b>Bulk (cm<sup>3</sup>/g)</b>	0.8-0.9	0.8-0.9	0.8-0.9	0.8-0.9	0.8-0.9	0.8-0.9	0.8-0.9	0.8-0.9

**Non-contractual data**

## PRESSPRINT O - Specifications

*Offset paper produced from chemical pulp (woodfree offset) or recycled fibres (recycled offset).*

*Offset printing with or without dryer.*

### WOODFREE OFFSET

<b>Grammage (g/m<sup>2</sup>)</b>	<b>70</b>	<b>80</b>	<b>90</b>	<b>100*</b>
<b>CIE whiteness (%)</b>	105	105	105	105
<b>ISO opacity (%)</b>	88	93	94	95
<b>Bulk (cm<sup>3</sup>/g)</b>	1.28	1.27	1.26	1.25

\* On request

### RECYCLED OFFSET

<b>Grammage (g/m<sup>2</sup>)</b>	<b>60</b>	<b>65</b>	<b>70</b>	<b>80</b>	<b>90</b>	<b>100</b>	<b>115</b>	<b>130 and +*</b>
<b>D65 whiteness (%)</b>	78	78	78	78	84	84	84	84
<b>ISO opacity (%)</b>	92	93	92-95	94-96	95-97	96-97	>98	>98
<b>Bulk (cm<sup>3</sup>/g)</b>	1-1.27	1-1.27	1-1.27	1-1.27	1-1.27	1-1.27	1-1.27	1-1.27

\* On request

### OFFSET WITH BULK

White, natural, ivory

Bulk (cm<sup>3</sup>/g): 1.5 – 1.8 – 2 – 2.2

Web and sheet fed

**Non-contractual data**